

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C08F 299/00, G02B 1/04		(11) International Publication Number: WO 92/09644
A1		(43) International Publication Date: 11 June 1992 (11.06.92)
(21) International Application Number: PCT/US91-08731 (22) International Filing Date: 20 November 1991 (20.11.91) (30) Priority data: 619,282 27 November 1990 (27.11.90) US (71) Applicant: BAUSCH & LOMB INCORPORATED [US/ US]; Patent Law Department, One Lincoln First Square, P.O. Box 54, Rochester, NY 14601-0054 (US). (72) Inventors: VALINT, Paul, L., Jr. ; 1 Farm Field Lane, Pitts- ford, NY 14534 (US). MCGEE, Joseph, A. ; 125 Terrace View Road, Dewitt, NY 13214 (US). LAI, Yu-Chin ; 23 Copper Woods, Pittsford, NY 14534 (US)		(74) Agents: POLYN, Denis, A. et al.; Bausch & Lomb Incor- porated, Patent Law Department, One Lincoln, First Square, P.O. Box 54, Rochester, NY 14601-0054 (US). (81) Designated States: AT (European patent), BE (European patent), BR, CA, CH (European patent), DE (European patent), DK (European patent), ES (European patent), FR (European patent), GB (European patent), GR (Eu- ropean patent), IT (European patent), JP, KR, LU (Eu- ropean patent), NL (European patent), SE (European patent). Published <i>With international search report.</i>
(54) Title: SURFACE MODIFICATION OF POLYMER OBJECTS		
(57) Abstract A method of modifying the surfaces of polymeric objects by adding a polymerizable surfactant to the monomer mix used to form the object. Also disclosed are surface-modified objects prepared by this method, which is particularly suited for modifying the surfaces of contact lenses.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MG	Madagascar
AU	Australia	FI	Finland	ML	Mali
BB	Barbados	FR	France	MN	Mongolia
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Faso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GN	Guinea	NL	Netherlands
BJ	Benin	GR	Greece	NO	Norway
BR	Brazil	HU	Hungary	PL	Poland
CA	Canada	IT	Italy	RO	Romania
CF	Central African Republic	JP	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SN	Senegal
CI	Côte d'Ivoire	LI	Liechtenstein	SU ⁺	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TG	Togo
DE*	Germany	MC	Monaco	US	United States of America
DK	Denmark				

+ Any designation of "SU" has effect in the Russian Federation. It is not yet known whether any such designation has effect in other States of the former Soviet Union.

SURFACE MODIFICATION OF POLYMER OBJECTSBACKGROUND OF THE INVENTION

5

The present invention is directed to modifying the surfaces of solid materials and more particularly to the use of polymerizable surfactants for such modifications.

10

Surface structure and composition determine many of the physical properties and ultimate uses of solid materials. Characteristics such as wetting, friction, electrostatic charging, and adhesion are largely
15 influenced by surface characteristics. Of particular concern are the effects of such surface characteristics on biocompatibility. The alteration of surface characteristics is therefore of special significance in biotechnical applications. Improved methods are
20 accordingly sought for modifying solid surfaces, particularly the surfaces of polymeric objects.

Random, grafted, polymerized surfactants have been used to modify the surfaces of hydrophobic polymers by
25 the adsorption of the surfactant onto the surfaces of polymeric objects from an aqueous dispersion. Lee, J. H., Interactions of PEO-Containing Polymeric Surfactants With Hydrophobic Surfaces, The University of Utah (1988) (hereinafter "Lee"). Lee--particularly
30 concerned with reducing the absorption of blood plasma proteins on hydrophobic surfaces--teaches the synthesis of polymeric surfactants by random free radical copolymerization of a hydrophobic methacrylate (hexyl methacrylate or lauryl methacrylate), a hydrophilic
35 methacrylate (polyethylene oxide methacrylate), and methyl methacrylate.

Akashi, M., et al., "Graft Copolymers Having Hydrophobic Backbone and Hydrophilic Branches. IV. A Copolymerization Study of Water-Soluble Oligovinylpyrrolidone Macromonomers," J. Polymer Sci.: Part A: Polymer Chemistry, Vol. 27, pp. 3521-3530 (1989) (hereinafter "Akashi") teaches amphiphiles prepared by random free radical copolymerization of carboxyl group-terminated oligovinylpyrrolidone with methyl methacrylate or styrene. Syntheses of vinylphenyl-terminated and methacryloyl-terminated oligovinylpyrrolidone macromonomers are described.

Polymerizable surfactants have been used to modify the properties of polymers in aqueous solution. For example, Schulz, et al., "Copolymers of Acrylamide and Surfactant Macromonomers: Synthesis and Solution Properties," Polymer, Vol. 28, pp. 2110-2115 (Nov., 1987) (hereinafter "Schulz") describes macromonomer surfactants wherein the surfactant character is achieved by the addition of a small hydrophobic functionality (e.g., nonylphenol) to a water-soluble polyethylene oxide chain. Related materials and methods are disclosed in U.S. Patent 4,075,411.

Polymerizable surfactants have also been used to modify the surface properties of solids. One class of materials used for this purpose are lipids (non-polymeric materials) which are rendered polymerizable by the addition of various functionalities such as methacrylate groups [Ringsdorf, H., et al., "Hydrophilic Spacer Groups in Polymerizable Lipids: Formation of Biomembrane Models from Bulk Polymerized Lipids," J. Am. Chem. Soc., Vol. 107, pp. 4134-4141 (1985)] and various vinyl groups [Ringsdorf, H., et al., "Saturated and Polymerizable Amphiphiles with Fluorocarbon Chains. Investigation in Monolayers and

Liposomes," J. Am. Chem. Soc., Vol. 106, pp. 7687-7692 (1984)]. These polymerizable lipid surfactants have been used to prepare liposomes used in the formation and stabilization of biomembrane models (often referred to as polymeric liposomes).

Contact lenses are conventionally produced by one of three general techniques--lathing, static casting, and spin casting. Combinations are also known. For example, semi-finished buttons (having one final lens surface) may be formed by static or spin casting and the second lens surface may be produced by lathing. Static and spin casting have the advantage of producing lenses with fewer processing steps than lathing. In either of the molding techniques, the anterior and posterior surfaces of the lens may be formed in one step. Static casting does this by providing two mold surfaces; spin casting does this by providing a mold surface to form the anterior surface and by using the forces generated by spinning liquid monomer to form the posterior surface.

One of the challenges faced when producing lenses by molding is achieving release of the lenses from the molds without damaging the lens surfaces. The phenomenon of lens adherence is a consequence of chemical interactions between mold surfaces and monomer mixtures during polymerization. Among the proposals to meet this challenge is U.S. Patent 4,534,916, which teaches adding (nonpolymerizable) surfactants to the monomer mix. The surfactant addition is reported to improve the surface quality of lenses by decreasing the number of surface defects resulting from mold release (especially of xerogel lenses).

The '916 patent seeks improved surface quality by reducing lens damage during demolding. Others have sought to improve surface quality more directly--by surface modifications. For example, U.S. 4,546,123 teaches covalent attachment of (nonpolymerizable) surfactant molecules to a hydrogel lens surface.

The macromonomer technique for preparing graft copolymers of controlled architecture is well known. Macromonomers or macromers are polymers of molecular weight ranging from the hundreds to tens of thousands, with one of the end groups functionalized to enter into further polymerization. Milkovich, Chiang and Schultz demonstrated the synthesis and applications of a variety of macromers. R. Milkovich, M.T. Chiang, U.S. Patent No. 3,842,050 (1974); Schultz, G.O. and Milkovich, R., J. App. Polym. Sci., 27, 4773 (1982); Schultz, G. O. & Milkovich, R., J. Polym. Sci. Polym. Chem. Ed., 22, 1633 (1984).

Yamashita, Y.; "Synthesis and Application of Fluorine Containing Graftcopolymers," Polymer Bull., 5, 335-340 (1981); "Synthesis and Characterization of Functional Graft Copolymers by Macromonomer Technique", J. Appl. Polym. Sci., 36, 193-199 (1981); "Synthesis of N-Hydroxyethyl-N-Methylmethacrylamide and Its Use in the Macromonomer Synthesis", J. Polym. Sci., Polym. Letters Ed., 19, 629-636 (1981); (hereinafter "Yamashita") teaches a method of making macromers and the use of macromers to make graft copolymers. Yamashita used free radical polymerization in the presence of an effective chain transfer agent which controlled the molecular weight of the final macromer and also provided a functional end group. Thioglycolic acid, for example, is an effective chain transfer agent which provides a carboxylic acid functional end group.


5

The end group can subsequently be reacted with, e.g., glycidyl methacrylate to give a terminal methacrylate polymerizable group. Yamashita used macromers of MMA to prepare graft copolymers of fluoroalkyl acrylates with polyMMA grafts. Yamashita does not teach the synthesis of polymerizable surfactants by the macromonomer technique.

10

SUMMARY OF THE INVENTION

It has now been found that the surface properties of a polymeric object may be modified by adding a polymerizable surfactant to the monomer mix used to form the polymeric object. While any polymerizable surfactant may be employed, a preferred class of polymerizable surfactants are novel surface active macromonomers described by the formula:



wherein A is at least one ethylenically unsaturated hydrophilic monomer, B is at least one ethylenically unsaturated hydrophobic monomer, C is a functional chain transfer agent, D is an ethylenically unsaturated end group, y is within the range from about 0.1 to about 0.9, and $x + y = 1$. In a preferred embodiment, the polymeric object is a contact lens.

30

DETAILED DESCRIPTION OF THE INVENTION


Notations such as "(meth)acrylate" or "(Meth)acrylamide" are used herein to denote optional methyl substitution. Thus, methyl (meth)acrylate includes both methyl acrylate and methyl methacrylate, and N-alkyl (meth)acrylamide includes both N-alkyl acrylamide and N-alkyl methacrylamide.

Polymerizable surfactants useful in the practice of this invention include any of the many polymerizable surfactants known to those skilled in the art.

- 5 Examples of such surfactants include: monofluoroalkyl esters of alkendioic acids, 2-(meth)acrylamido-2-alkylethane-1-sulfonic acid, α,ω -(meth)acrylamidoalkanoic acid, dimethylhexadecyl[11-(methacryloyloxy)undecyl]ammonium halide,
- 10 dimethylhexadecyl[11-(methacryloyloxy)undecyl]ammonium dimethyl phosphate, 1-palmitoyl-2-[11-(methacryloyloxy)undecyl]-*sn*-glycero-3-phosphocholine, 1,2-bis[11-(methacryloyloxy)undecyl]-*sn*-glycero-3-phosphocholine, 1,2-bis(heptadeca-10,12-diynoyl)-*sn*-
- 15 glycero-3-phosphocholine, 1,2-bis(heneicosa-10,12-diynoyl)-*sn*-glycero-3-phosphocholine, 1,2-bis(hexacosa-10,12-diynoyl)-*sn*-glycero-3-phosphocholine, bis[10-(methacryloyloxy)decyl] hydrogen phosphate, bis[11-(methacryloyloxy)undecyl]dimethylammonium halide and
- 20 bis[11-(methacryloyloxy)undecyl]dimethylammonium dimethyl phosphate.

Particularly preferred polymerizable surfactants useful in the process of this invention are surface

25 active macromonomers described by the formula:



wherein A is at least one ethylenically unsaturated hydrophilic monomer, B is at least one ethylenically unsaturated hydrophobic monomer, C is a functional

30 chain transfer agent, D is an ethylenically unsaturated end group, y is within the range of about 0.1 to about 0.9, and $x + y = 1$.

Suitable ethylenically unsaturated hydrophilic

35 monomers ("A" in the above formula) include ethylenically unsaturated polyoxyalkylenes,

polyacrylamides, polyvinylpyrrolidones, polyvinyl
alcohols, poly (hydroxyethyl methacrylate) or poly
(HEMA), and N-alkyl-N-vinyl acetamides. Ethylenic
unsaturation may be provided by (meth)acrylate,
5 (meth)acrylamide, styrenyl, alkenyl, vinyl carbonate
and vinyl carbamate groups. Preferred hydrophilic
macromonomers include methoxypolyoxyethylene
methacrylates of molecular weights from 200 to 10,000,
more preferred are methoxypolyoxyethylene methacrylates
10 of molecular weight range of 200 to 5,000 and most
preferred are methoxypolyoxyethylene methacrylates of
molecular weight range of 400 to 5,000. Additional
preferred hydrophilic macromonomers include poly-N-
vinylpyrrolidone methacrylates of molecular weights of
15 500 to 10,000. More preferred are poly-N-
vinylpyrrolidone methacrylates of molecular weights of
500 to 5,000 and most preferred are poly-N-
vinylpyrrolidone methacrylates of molecular weights of
1000 to 5,000. Other preferred hydrophilic
20 macromonomers include poly-N,N-dimethyl acrylamide
methacrylates of molecular weights of 500 to 10,000.
More preferred are poly-N,N-dimethyl acrylamide
methacrylates of molecular weights of 500 to 5,000 and
most preferred are poly-N,N-dimethyl acrylamide
25 methacrylates of molecular weights of 1000 to 5,000.

Suitable ethylenically unsaturated hydrophobic
monomers ("B" in the above formula) include alkyl
(meth)acrylates, N-alkyl (meth)acrylamides, alkyl
30 vinylcarbonates, alkyl vinylcarbamates, fluoroalkyl
(meth)acrylates, N-fluoroalkyl (meth)acrylamides, N-
fluoroalkyl vinylcarbonates, N-fluoroalkyl
vinylcarbamates, silicone-containing (meth)acrylates,
(meth)acrylamides, vinyl carbonates, vinyl carbamates,
35 styrenic monomers [selected from the group consisting
of styrene, alpha-methyl styrene, para-methyl styrene,

para-t-butyl monochloro styrene, and para-t-butyl dichloro styrene] and polyoxypropylene (meth)acrylates. Preferred hydrophobic monomers include methyl methacrylate, dodecyl methacrylate, octafluoropentyl methacrylate, perfluorooctyl methacrylate, methacryloyl oxypropyl tris(trimethylsiloxy)silane (TRIS).

The functional chain transfer agent ("C" in the above formula) controls the molecular weight of the copolymer and provides appropriate functionality for subsequent addition of a polymerizable group. Suitable functional chain transfer agents include mercapto carboxylic acids, mercapto alcohols (also known as hydroxymercaptans), and aminomercaptans. Preferred chain transfer agents include thioglycolic acid, 2-mercaptoethanol and 2-aminoethane thiol. The molar ratio of chain transfer agent to total monomer used in the copolymerization is preferably about 0.01 to about 3, more preferably about 0.02 to about 2, and still more preferably about 0.05 to about 1.

Selection of the ethylenically unsaturated end group ("D" in the above formula) is determined by the functional group of the functional chain transfer agent. For example, if the chain transfer agent contains a carboxylic acid group, glycidyl methacrylate can provide a methacrylate end group. If the chain transfer agent contains hydroxy or amino functionality, isocyanato ethyl methacrylate or (meth)acryloyl chloride can provide a methacrylate end group and vinyl chloro formate can provide a vinyl end group. Other combinations will be apparent to those skilled in the art.

Varying the ratio of hydrophilic monomer to hydrophobic monomer changes the surface properties of

polymeric objects made from the surface active macromers. For example, when preparing contact lenses containing certain surface active macromers of this invention, it has been found that higher amounts of hydrophilic component optimized mold release characteristics of the lenses but that optimum clinical performance was obtained with a relatively lower amount of hydrophilic component. Accordingly, the selection of a particular ratio will be governed by the particular surface properties ultimately sought for the polymeric object. Generally, however, y is preferably in the range from about 0.1 to about 0.9, more preferably in the range from about 0.3 to about 0.9, and still more preferably in the range from about 0.5 to about 0.8.

The random copolymers, from which the surface-active macromers are derived, are prepared by copolymerizing at least one ethylenically unsaturated hydrophobic monomer and at least one ethylenically unsaturated hydrophilic monomer in the presence of a functional chain transfer agent. The random copolymers are formed by a free radical mechanism using a wide variety of known free radical catalysts such as the diacyl peroxides (e.g., benzoyl peroxide); dialkyl peroxides (e.g., di-tert-butyl peroxides); ketone peroxides (e.g., methylethyl ketone peroxide); and peresters which readily hydrolyze (e.g., tert-butyl peracetate, tert-butyl perbenzoate, di-tert-butyl diperphthalate). A particularly useful class of peroxy initiators are the organic hydroperoxides such as cumene hydroperoxide, methylethyl ketone hydroperoxide, tert-butyl hydroperoxide, etc. The initiators should be used at a concentration of about 0.01 to about 10% by weight of the total formulation, preferably about 0.1 to about 5%. Another class of initiators comprises

carbonyl-containing ultraviolet-activated free radical generators, such as acetophenone, benzophenone, and benzoin ethers. Other suitable UV initiators and initiator mixtures will be apparent to one of ordinary skill in the art. Solvents can be used in the process. Solvent choice will depend upon the solubility parameters of the comonomers used and should be chosen to allow full solubilization of all polymerizable components. Preferred solvents include tetrahydrofuran, dioxane, chloroform, dichloromethane, methanol and mixtures of these solvents.

The polymerizable surfactants, including the surface-active macromers, described above may be used to modify the surfaces of polymeric objects by adding the polymerizable surfactant to the monomer mix used to form the polymeric object. The amount added to a monomer mix is usually kept at a relatively low level sufficient to obtain the desired surface property modification without significantly affecting the bulk properties of the polymeric object. Therefore, the preferred concentration of polymerizable surfactant utilized in this invention is from 0.025 weight % to 10 weight %. A more preferred concentration range is 0.05 to 8 weight % and the most preferred range is 0.1 to 5 weight %.

The polymeric objects whose surfaces may be modified by these techniques include polymers having a wide variety of compositions and shapes. Polymeric objects of particular concern in the development of this invention were contact lenses and the particular surface modification sought was to increase surface wettability without sacrificing otherwise beneficial bulk properties of the polymeric material (especially oxygen permeability). Although the utility of the

macromonomers of this invention will be further illustrated by referring particularly to their incorporation into contact lenses, it will be understood that the utility of the macromonomers of this invention is not so limited.

One class of contact lenses whose surface may be usefully modified by the macromonomers of this invention are soft hydrogel lenses. Conventional monomer systems for such lenses employ a hydrophilic monoolefinic monomer (i.e., a monoethylenically unsaturated monomer) and a polyolefinic (usually diolefinic) monomer (e.g., a polyethylenically unsaturated compound which functions as a cross-linking agent) in an amount sufficient to insolubilize the resulting hydrophilic hydrogel but insufficient to destroy the hydrophilic properties. Mixtures of hydrophilic monoolefinic monomers are used as well as mixtures of cross-linking agents. Other monomers which are copolymerizable with the hydrophilic monomer are also used to adjust various properties of the polymeric material, as is well known in the art.

Illustrative hydrophilic monomers include water soluble monoesters of (meth)acrylic acid with an alcohol having an esterifiable hydroxyl group and at least one additional hydroxyl group such as the mono- and poly-alkylene glycol monoesters of (meth)acrylic acid, e.g., ethylene glycol mono(meth)acrylate, diethylene glycol mono(meth)acrylate, propylene glycol mono(meth)acrylate, dipropylene glycol mono(meth)acrylate, and the like; the N-alkyl and N,N-dialkyl substituted (meth)acrylamides such as N-methyl (meth)acrylamide, N,N-dimethyl (meth)acrylamide, and the like; N-vinylpyrrolidone and the alkyl substituted N-vinyl pyrrolidones; glycidyl (meth)acrylates; the

unsaturated amines; the alkoxy ethyl acrylates; mixtures thereof; and others known to the art.

5 Illustrative di- or higher polyfunctional species employed as cross-linking agents are divinylbenzene, ethylene glycol di(meth)acrylate, propylene glycol di(meth)acrylate, and the (meth)acrylate esters of polyols such as triethanolamine, glycerol, pentaerythritol, butylene glycol, diethylene glycol, 10 triethylene glycol, tetraethylene glycol, mannitol, and sorbitol. Further illustrations include N,N-methylene-bis-(meth)acrylamide, sulfonated divinylbenzene, and divinylsulfone.



15 Illustrative of other copolymerizable monomers are hydrophobic (meth)acrylic esters such as alkyl (meth)acrylates wherein the alkyl moiety contains 1-5 carbon atoms.

20 While soft, hydrophilic, gel-type lenses may be modified by the macromonomers of this invention, of greater interest is the modification of lenses prepared from a formulation including at least one silicone monomer and at least one hydrophilic monomer. Included 25 in this class of materials are soft contact lens formulations (both hydrogel and nonhydrogel) and rigid gas permeable contact lens formulations.

Preferred soft hydrogel formulations are those 30 described in U.S. Patent Application Serial Nos. 07/363,662 filed June 7, 1989 and 07/364,204 filed May 2, 1989, the entire contents of which are incorporated herein by reference. Other examples of useable formulations are found in U.S. Patent 35 Nos. 4,136,250; 4,740,533 4,711,943; 4,189,546; and 4,153,641.


One type of presently preferred hydrogel formulations incorporate urethane prepolymers of the general formula:

5



where

A denotes a divalent polymeric radical represented by the general formula chosen from the group of




wherein R^S denotes an alkyl radical or a short chain fluorinated alkyl radical with 1 to 3 carbon atoms; and

p provides a moiety weight of 400 to 10,000;
D denotes an alkyl diradical, an alkyl cycloalkyl diradical, a cycloalkyl diradical, an alkylaryl diradical or an aryl diradical, with 6 to 30 carbon atoms;

G denotes an alkyl diradical, a cycloalkyl diradical, an alkyl cycloalkyl diradical, an aromatic diradical or an alkylaromatic diradical with 1 to 40 carbon atoms which may have ether, thio, or amine linkages in the main chain;

* denotes a urethane or ureido linkage; and

E and E' denote polymerizable unsaturated organic radicals represented by the general chemical formula



R^2 denotes a -H or -CH₃ radical;

35

R^3 denotes a -H radical or an alkyl radical with 1 to

6 carbon atoms or a $\overset{\text{O}}{\parallel}\text{-CY-R}^4$ radical where
 5 Y is -O-, -S- or -NH- and R^4 denotes an
 alkyl radical with 1 to 12 carbon
 atoms;

X denotes $\overset{\text{O}}{\parallel}\text{-C-}$, or $\text{-O-}\overset{\text{O}}{\parallel}\text{C-}$;

10 Z denotes -O-, -S-, or -NH-;

Ar denotes an aromatic radical with 6 to 30 carbon
 atoms;

a is at least 1;

w is 0 to 6;

15 x is 0 or 1;

y is 0 or 1; and


z is 0 or 1.

The isocyanates which can be used in preparation of
 20 these urethane prepolymers include toluene
 diisocyanate, 4,4'-diphenyl diisocyanate, 4,4'-
 diphenylene methane diisocyanate, p-phenylene
 diisocyanate, dianisidine diisocyanate, 1,5 naphthalene
 diisocyanate, 4,4'-diphenyl ether diisocyanate,
 25 4,4'(dicyclohexyl)methane diisocyanate, 1,3-bis-
 (isocyanato methyl)cyclohexane, cyclohexane
 diisocyanato, tetrachlorophenylene diisocyanate,
 isophorone diisocyanate, and 3,5-diethyl-4,4'-
 diisocyanato diphenyl methane.

30

Other diisocyanates which may be used are higher
 molecular weight diisocyanate formed by reacting
 polyamines which are terminally capped with primary or
 secondary amines, or polyhydric alcohols with excess of
 35 any of the above described diisocyanates. In general,

these high molecular weight diisocyanates will have the general formula



wherein R is a divalent organic radical with 2 to about 20 carbon atoms, X is -O-, or -NR'-, where R is -H or a lower alkyl, and B is a divalent organic radical.

10




The diisocyanate is reacted with low molecular weight diols or glycols such as 2,2-(4,4'-dihydroxydiphenyl)-propane (bisphenol-A), 4,4'-isopropylidene dicyclohexanol (hydrogenated biphenol-A),
 15 ethoxylated bisphenol-A, propoxylated bisphenol-A, 2,2-(4,4'-dihydroxydiphenyl)-pentane, α,α' -(4,4'-dihydroxydiphenyl)-p-diisopropyl benzene, 1,3-cyclohexane diol, 1,4-cyclohexane diol-1,4-cyclohexane dimethanol, bicyclic and tricyclic diols such as 4,8-
 20 bis-(hydroxymethyl)-tricyclo [5.2.1.0^{2,6}] decane, neopentyl glycol, 1, 4 butanediol, 1,3-propanediol, 1,5-pentanediol, diethylene glycol, triethylene glycol and the like.

25

These hard segments form hard domains in the final polymer or copolymer by association via hydrogen bonding with other rigid segments. The degree of association within the hard domain can be modified by controlling the amount of hydrogen bonding between the
 30 segments by either 1) decreasing the overall weight content of the hard segment in the prepolymer by increasing the molecular weight of the soft segment or 2) by decreasing the amount of hydrogen bonding density in the hard segment by either using relatively soft,
 35 longer chained diols, or by using primary amines or secondary amines capped low molecular weight compounds

in conjunction with the diisocyanates rather than the diols.

The hard segments are then reacted with a relatively high molecular weight polymer which is α, ω -endcapped with two active hydrogens, usually hydroxyl groups. These segments form the so-called soft segment of the prepolymer. Various types of high molecular weight polymers can be used including in general polymers of the following formulae




Formulae a) represents polyoxyalkyleneglycols. These diols include polymers prepared from the epoxides: ethylene oxide 1,2-propylene oxide, 1,2-butylene oxide, 2,2 epoxydecane, 1,2-epoxyoctane, 2,3-epoxy norborane, 1,2-epoxy-3-ethoxy propane, 2,2-epoxy-3-phenoxypropane, 2,3-epoxypropyl-4-methoxy phenyl ether, tetrahydrofluran, 1,2-epoxy-3-cyclohexyloxy propane, oxetane, 1,2-epoxy-5-hexene, 1,2-epoxyethylbenzene, 1,2-epoxy-1-methoxy-2-methylpropane, benzyloxy propylene oxide, the like and combinations thereof.

The preferred polymers of this class are polypropylene glycols of molecular weights, 2000, 3000 and 4000 and more and polyoxyethylene polyoxypropylene block copolymers with molecular weight greater than 2000.

Formulae b) represents polyfluoroethers with α, ω -active hydrogens. This class of polymers can be synthesized as taught in U.S. Patent No. 3,810,874. Generally, these polymers should have molecular weights
 5 between 400 and 10,000.

Formulae c) represents α, ω - dihydroxyl alkyl endblocked polysiloxane which for the purpose of the present invention should have a molecular weight in the
 10 range of 400 to 10,000. These polysiloxanes can be synthesized by reacting a disiloxane of the general formula




with cyclopolydimethyl siloxane under acidic conditions.

20

Alternately, the disiloxane can be replaced with dimethoxydimethylsilane or diethoxy dimethyl silane to produce the α, ω - dihydroxy endcapped polysiloxanes.

25 The endcapping monomers used in the prepolymer are generally represented by the formula



as defined supra. The Stage B reaction product is reacted with an excess of suitable acrylate or methacrylate esters containing a hydroxy or amine group on the non-acrylate or non-methacrylate portion of the
 35 monomer to form the endcaps of the above formula. Suitable endcap monomers include hydroxyethyl acrylate,

hydroxyethyl methacrylate, aminoethyl methacrylate, 3
 hydroxypropyl methacrylate, amino propyl methacrylate,
 hydroxyhexylacrylate, t-butylaminoethyl methacrylate,
 monoacrylate or monomethacrylate esters of bisphenol-A
 5 and/or bisphenol-B.

The urethane prepolymers are formed by two general
 synthetic approaches. One approach produces the hard-
 soft-hard prepolymer while the second approach produces
 10 the soft-hard-soft prepolymer.

The scheme used to produce hard-soft-hard urethane
 prepolymer employed three stages. In the first stage
 (STAGE A) 2 mole equivalents of diisocyanate are
 15 reacted with about 1 mole equivalent low molecular
 weight diols. If these diols are represented by the
 symbol $\diamond G \diamond$, where \diamond denotes a hydroxyl radical and G
 represents the rest of the diol compound, and the
 diisocyanate functional compound is represented by $\bullet D \bullet$
 20 where \bullet represents an isocyanate radical, the STAGE A
 reaction can be schematically represented as follows:



25 where $*$ denotes a urethane or a ureido linkage. STAGE
 A produces a so-called "Hard" segment. As is known to
 those skilled in polymer chemistry, the product $\bullet D * G * D \bullet$
 is the mathematical average of all reaction product
 molecules. The reaction product of the actual reaction
 30 will contain $\bullet O \bullet$ and $\bullet D (* G * D)_c * G * D$ with $c \geq 2$. Again,
 the formulas are numerical averages.

STAGE B involves reacting about one half mole
 equivalent of a α, ω - diol endcapped long chain polymer
 35 with the reaction product of STAGE A. If $\diamond A \diamond$
 represents the long chain diol the STAGE B Reaction is



In STAGE C, the reaction product from STAGE B is
 5 reached with a molar excess of an endcapping monomer
 which has: 1) hydroxyl or amine functionality; and 2)
 some polymerizable unsaturation. If the endcapper is
 represented by the symbol $E \cdot$, where \cdot is $-OH$ or $-NH_2$ or
 $-NH-$, the reaction proceeds generally as

10




Optionally, STAGE B can be run with molar excess of
 $\cdot A \cdot$ to produce multiblock polymers of the general
 15 formula $\cdot (D \cdot G \cdot D \cdot A)_a \cdot D \cdot G \cdot D \cdot$ where a is at least 1. This
 reaction product would be endcapped in STAGE C above.


The second general synthetic scheme using the same
 nomenclature described is represented by the following
 20 general formulae:

STAGE A

25




STAGE B



30

STAGE C



In general, each of the reaction stages is run until
 35 the reactive step is complete. Reaction progress in
 STAGES A and B reaction can be monitored by acid base

titration. The isocyanate content was calculated by the difference of acid equivalents between a stock solution dibutylamine and its reaction product with the diisocyanate reaction intermediate. The reaction was also monitored by ATR-IR for the appearance/disappearance of peaks at 1700 cm^{-1} , which indicated the presence of

$\begin{array}{c} \text{O} \\ \parallel \\ -\text{C}- \end{array}$, and 2250 cm^{-1} which indicated consumption of $-\text{N}=\text{C}=\text{O}$.

The synthesis of the prepolymer may be run neat or in solution. A wide range of aprotic solvents can be used to synthesize the prepolymers of the present invention. Solvents useful in the synthesis include toluene, methylene chloride, benzene, cyclohexane, hexane, heptane and the like. Preferred solvents are toluene, methylene chloride and mixtures thereof.

Reaction of the prepolymer precursors may be accomplished in the presence or absence of catalysts for urethane reactions, such catalysts being well known in the art. The first step of prepolymer synthesis where diisocyanate is first reacted with a short carbon chain (2 to 30 carbon atoms) diol, particularly where an aromatic diisocyanate is used, proceeds very rapidly, even in the absence of any catalyst. In fact, during the step of reacting diisocyanate and short chain diol, temperature control may be required in order to avoid/minimize side reactions.


Preferably, the first step of prepolymer synthesis in accordance with the present invention is carried out below about 100°C , most suitably within the range of from about 60°C to about 90°C . Thereafter, the second step of the reaction is carried out at comparable

temperatures, preferably within the range of from about 40°C to 70°C. The final step of prepolymer formation suitably is effected at temperatures of from about room temperature to about 100°C, with a narrow range of from about 40°C to about 50°C being most preferred. As will be apparent to those skilled in the art, optimal reaction conditions, such as temperatures and duration, are selected for each individual reaction system to achieve conditions that produce a favorable rate of reaction without fostering undesirable side reactions.

Among the suitable catalysts for use in prepolymer formation are tin salts and organic tin esters, such as dibutyl tin dilaurate, tertiary amines, such as triethyl diamine and other recognized catalysts, such as 1,4-diaza (2.2.2)-bicyclooctane (DABCO).

These silicone-containing urethane prepolymers may be copolymerized with a wide variety of hydrophilic monomers to produce soft hydrogel contact lenses. Hydrophilic monomers suitable for this use include 2-hydroxyethylmethacrylate, N-vinyl pyrrolidone, (meth)acrylamide, vinyl acetamide, and other ethylenically unsaturated hydrophilic monomers. Further comonomers may also be added to enhance wetting or to modify other properties as is generally known to those skilled in the art.

Another presently preferred hydrogel formulation incorporates silicone-containing vinyl carbonate or vinyl carbamate prepolymers of the general formula:



wherein X denotes an -O-, -S-, or -NR³- divalent radical;

R^{Si} denotes a silicone containing organic radical;


5 R² denotes -H or -CH₃;

A is 1, 2, 3, or 4; and


b is 0 or 1.

Suitable silicone-containing organic radicals (R^{Si}) include the following:


10



15




20



where R¹ denotes a monovalent organic radical such as an alkyl radical with 1 to 6 carbon atoms, or a
25 fluoroalkyl radical with 1 to 6 carbon atoms;

R^{Cl} denotes



p is 1 to 6; and

d is 1-200, and


30 where n is 1, 2, 3, or 4, and m is 0, 1, 2, 3, 4, or 5.

The silicone-containing vinyl carbonate/carbamate monomers specifically include

3-[tris(trimethylsiloxy)silyl]propyl vinyl carbonate;
1,3-bis[4-(vinylloxycarbonyloxy)but-1-yl]tetramethyl-dis
5 iloxane; 3-(trimethylsilyl)propyl vinyl carbonate;
t-butyldimethylsiloxyethyl vinyl carbonate;
trimethyl-silylmethyl vinyl carbonate;
trimethylsilylethyl vinyl carbonate;
2,2,2-trifluoroethyl vinyl carbonate; t-butyl vinyl
10 carbonate; 3-[tris(trimethylsiloxy)silyl] propyl vinyl
carbonate; 2,2,2-trifluoroethyl vinyl carbamate;
1,1,1,3,3,3-hexafluoro-2-propyl vinyl carbonate;
3-(vinylloxycarbonylthio)propyl-[tris(trimethylsiloxy)si
lane]; 3-[tris-(trimethylsiloxy)silyl]propyl vinyl
15 carbamate; "V₂D₂₅", 2,2,2-trifluoro-1-phenylethyl vinyl
carbonate; 1-adamantane vinyl carbonate,
1-adamantanethyl vinyl carbonate, 1-adamantaneethyl
vinyl carbonate; and 1-adamantane vinyl carbamate.


20 Preferred nonhydrogel soft contact lens
formulations are mixtures of polymerizable
polysiloxanes containing fluorinated side chains and
internal wetting agents. Further components such as
toughening agents, crosslinking agents, and other
25 auxiliary modifiers are desirably present as taught in
U.S. Patent 4,810,764, the entire content of which is
incorporated herein by reference.

Polymerizable, fluorinated polysiloxanes employed
30 in this embodiment of the invention are described by
the general formula:



5 where A denotes an activated unsaturated group, $-R^1$ and R^2 independently denote alkyl radicals with 1 to 6 carbon atoms or phenyl radicals; R^3 and R^4 independently denote alkyl radicals with 1 to 6 carbon atoms, phenyl radicals, or fluorinated alkyl radicals
10 with 1 to 6 carbon atoms, provided that at least one of R^3 or R^4 is a fluorinated alkyl radical with 1 to 6 carbon atoms; $m + n$ is at least 1; and n is at least 1.

15 Internal wetting agents ("hydrophilic monomers") useful in this embodiment of the invention include N-alkylenoyl trialkylsilyl aminates (hereinafter "NATA") (described in U.S. Patent No. 4,652,622) represented by
20 the general formula




wherein

- E is H or CH_3 ,
- G is $(CH_2)_x C(O)OSi(R)_3$ or H,
- 25 R is CH_3 , C_2H_5 or C_3H_7 ,
- m is an integer from 1 to 15,
- x is an integer from 1 to 10, and
- m + x is an integer from 1 to 15

30 Acryloyl- and methacryloyl-, mono- and dicarboxylic amino acids, hereinafter NAA, impart desirable surface wetting characteristics to polysiloxane polymers, but precipitate out of siloxane monomer mixtures before polymerization is completed. NAA can be modified to form trialkylsilyl esters which are more readily

incorporated into polysilocane polymers. The preferred NATA's are trimethylsilyl-N-methacryloylglutamate, triethylsilyl-N-methacryloylglutamate, trimethyl-N-methacryloyl-6-aminohexanoate, trimethylsilyl-N-methacryloyl-aminododecanoate, and bis-trimethylsilyl-N-methacryloyl aspartate.

The preferred internal wetting agents are oxazolones of the general formula



where

R_1 and R_2 independently denote H or CH_3 ; and

R_3 and R_4 independently denote methyl or cyclohexylradicals.

These preferred internal wetting agents specifically include

2-isopropenyl-4,4-dimethyl-2-oxazolin-5-one (IPDMO),

2-vinyl-4,4-dimethyl-2-oxazolin-5-one (VDMO),

cyclohexane spiro-4'-(2'-isopropenyl-2'-oxazol-5'-one)

(IPCO),



cyclohexane-spiro-4'-(2'-vinyl-2'-oxazol-5'-one) (VCO),


and 2-((-isopropenyl)-4,4 dimethyl-oxazol-5-one (PDMO).

These preferred internal wetting agents have two important features which make them particularly desirable wetting agents: (1) they are relatively non-polar and are compatible with the hydrophobic monomers (the poly siloxanes and the toughening agents), and (2) they are converted to highly polar amino acids on modification with a suitable surfactant wetting characterizing the polymerized product in the presence of the surfactant. These

internal wetting agents result through the carbon-carbon double bond with the endcaps of the polysiloxane monomers, and with the toughening agents to form copolymeric materials particularly useful in biomedical devices, especially contact lenses.

These oxazolones are prepared by the general reaction sequence





10 The first step is a Shotten-Bauman acrylation of an amino acid. Upon completion of this step the polymerizable functionality is introduced by using either acryloyl or methacryloyl chloride.

15 Rigid gas permeable contact lens formulations which are suitable for the practice of this invention are silicone-based copolymers prepared from siloxanylalkyl esters of methacrylic acid and other acrylate, methacrylate, or itaconate monomers in many known formulations. See U.S. Patent Nos. 4,424,328;
20 4,463,149; 4,664,479; and 4,686,267 for examples of such formulations.

This invention is further described by the following Examples which are intended to be
25 illustrative, not limiting.

EXAMPLES

30

EXAMPLE 1

Polymerization of 1-Vinyl-2-pyrrolidinone

Distilled 1-vinyl-2-pyrrolidinone (NVP), 40 g, 2- mercaptoethanol, 2.80 g, and azobisisobutyronitrile (A BN, recrystallized from ethanol), 0.59 g, were
35 combined with 100 ml of anhydrous tetrahydrofuran (THF)

in a 250 mL three-neck flask. The flask was also fitted with a mechanical stirrer and a reflux condenser. A slow stream of nitrogen was used to deoxygenate the solution for 15 minutes. After 5 24 hours of reflux under a nitrogen atmosphere, no vinyl protons could be detected in the 60 Mhz NMR spectra (6.5-7.0 ppm). The hydroxy-terminated polymer was precipitated from 2 L of anhydrous ethyl ether. The solid was dissolved in 200 ml of THF and the 10 precipitation repeated twice. The white solid, 29.37 g (69% yield), was dried under reduced pressure.

EXAMPLE 2

15 Synthesis of a Polyvinyl Pyrrolidinone (PVP) Macromer

Hydroxy-terminated PVP, 9.0 g (from Example 1), was dissolved in 90 mL of chloroform, in a 250 mL 3-neck flask fitted with a magnetic stirrer, a reflux 20 condenser, and an addition funnel. Dibutyltin dilaurate, 32.5 mg, and butylated hydroxy toluene, 2.1 mg (BHT), were added. Isocyanatoethyl methacrylate, 0.86 g (ICEM) in 10 mL CHCl_3 , was added dropwise. Following the addition the solution was 25 heated to reflux. After 3 hours no ICEM could be detected by infrared analysis. The reaction mixture was then slowly added to 6 L of anhydrous ethyl ether and the solid collected. Precipitation of the PVP macromer was repeated, from ethanol into 4 L of ethyl 30 ether. After drying at 30°C under reduced pressure the yield of macromer was 7.1 g (78%). The M_n (number average molecular weight) and P_d (polydispersity) values were 1.486 and 1.4 (vs. polyethylene glycol standards).

EXAMPLE 3

Copolymerization of OFPMA and PVP Macromer

1H,1H,5H Octafluoropentylmethacrylate, (OFPMA)
5 0.75 g, PVP macromer (Example 2), 5.0 g,
2-mercaptoethanol, 105 uL, and AIBN (recrystallized
from ethanol), 8.2 mg, were combined with 100 mL of
anhydrous tetrahydrofuran (THF) in a 250 mL three neck
10 flask. The flask was also fitted with a mechanical
stirrer and a reflux condenser. A slow stream of
nitrogen was used to deoxygenate the solution for
15 minutes. After 20 hours of reflux under a nitrogen
atmosphere the hydroxy terminated polymer was
precipitated from 2 L of anhydrous ethyl ether. The
15 solid was dissolved in 200 ml of THF and the
precipitation repeated once. The white solid was dried
under reduced pressure leaving 4.14 g, a 72% yield.

20

EXAMPLE 4

Polymerization of N,N-Dimethylacrylamide(DMA)

Distilled DMA, 20 g, 2-mercaptoethanol, 280 uL,
and AIBN (recrystallized from ethanol), 0.33 g, were
25 combined with 100 mL of anhydrous tetrahydrofuran (THF)
in a 250 mL three neck flask. The flask was also
fitted with a mechanical stirrer and a reflux
condenser. A slow stream of nitrogen was used to
deoxygenate the solution for 15 minutes. After
30 20 hours of reflux under a nitrogen atmosphere no vinyl
protons could be detected in the 60 Mhz NMR spectra
(6.5-7.0 ppm). The hydroxy terminated polymer was
precipitated from 2 L of anhydrous ethyl ether. The
solid was dissolved in 100 ml of THF and the
35 precipitation repeated. The white solid was dried
under reduced pressure at 30°C. The yield was 15.5 g

and the Mn (number average molecular weight), Mw (weight average molecular weight) and Pd (polydispersity) values were 6,700, 11,318 and 1.7 (vs. polyethylene glycol standards).

5

EXAMPLE 5

Preparation of a DMA Macromonomer

10 Hydroxy terminated copolymer, 12 g (from Example 4), was dissolved in 90 mL of chloroform, in a 250 mL 3-neck flask fitted with a magnetic stirrer and a reflux condenser and an addition funnel. Dibutyltin dilaurate, 36.9 mg, and butylated hydroxy toluene
15 (BHT), 10.2 mg, were added. Isocyanatoethyl methacrylate, 0.30 g (ICEM) in 10 mL CHCl_3 , was added dropwise. Following the addition the solution was heated to reflux. After 48 hours no ICEM could be detected by infrared analysis. The reaction mixture
20 was then slowly added to 2 L of anhydrous ethyl ether and the solid collected. The precipitation was repeated a second time followed by drying at 30°C under reduced pressure. The yield of macromer was 8.6 g. The Mn, Mw and Pd values were 4,400, 7,900 and 1.8 (vs.
25 polyethylene glycol standards).

EXAMPLE 6

Copolymerization of OFPMA and DMA Macromer

30 OFPMA, 1.2 g, DMA macromer (Example 5), 6.7 g 2-mercaptoethanol, 105 uL, and AIBN (recrystallize from ethanol), 8 mg, were combined with 100 mL of
35 anhydrous tetrahydrofuran (THF) in a 250 mL three-neck flask. The flask was also fitted with a magnetic

stirrer and a reflux condenser. A slow stream of nitrogen was used to deoxygenate the solution for 15 minutes. After 72 hours of reflux under a nitrogen atmosphere the conversion to copolymer was 44%, (by NIR analysis). Addition of 25 mg AIBN and 48 hours refluxing, (120 hours total) gave a 60% conversion to copolymer. Precipitation into 2 L of anhydrous ethyl ether, followed by drying at reduced pressure left 6 g of copolymer with Mn, Mw, and Pd values of 4,600, 8,100, and 1.8 (vs. PEG standards).

EXAMPLES 7-10

Copolymerization of 1H,1H,5H
Octafluoropentylmethacrylate
and Methoxy polyethylene glycol monomethacrylates

Example 7

A solution was prepared by dissolving 9.1 g of methoxy polyethylene glycol 1,000 monomethacrylate in 100 mL of toluene. The solution was carefully transferred to a 250 mL three neck flask fitted with a magnetic stirrer and a condenser. To this, 9.1 g of 1H,1H,5H Octafluoropentylmethacrylate (OFPMA), 1.26 g of distilled thioglycolic acid (TGA) and 0.071 g of azobisisobutyronitrile (AIBN) were added. AIBN was recrystallized from ethanol before use. The solution was then deoxygenated using nitrogen for 15 minutes and then placed under a passive nitrogen blanket. After stirring for 16 hours at 60°C the percent conversion was determined to be 95-98% by near infrared (NIR) analysis. The number average molecular weight was determined by size exclusion chromatography ("SEC") vs. polystyrene and by end group titration. The Mn values were 2,902 and 1,815 respectively. Results are shown in Table I.

Examples 8-9

5 The procedure of Example 7 was repeated using
higher relative amounts of methoxy polyethylene glycol
1000 monomethacrylate. THF replaced toluene as the
solvent in Example 9. Results are shown in Table I.

Example 10

10 The procedure of Example 7 was repeated using
methoxy polyethylene glycol 5000 monomethacrylate and
using THF as the solvent. Results are shown in
Table I.

15

Table IACID TERMINATED COPOLYMERS

Example #	Type	Composition	Solvent	Rxn time	Mn	Mw	Pd
5	7	80/20	Toluene	16h	2902	5370	1.8
	8	70/30	Toluene	72h	2300	3400	1.44
10	9	50/50	THF	24h	3163	5287	1.7
	10	80/20	THF	24h	12.6k	9400	1.34

EXAMPLE 11

5 Copolymerization of
 3-Methacryloyloxypropyltris(trimethylsiloxy)silane
 and Methoxy polyethylene glycol 1,000 monomethacrylate

 A solution was prepared by dissolving 7.1 g of
methoxy polyethylene glycol 1,000 monomethacrylate in
10 100 ml of toluene. The solution was carefully
transferred to a 250 ml three-neck flask fitted with a
magnetic stirrer and a condenser. To this, 12.8 g of
3-methacryloyloxypropyltris(trimethylsiloxy)silane
(TRIS), 1.0 g of distilled thioglycolic acid (TGA) and
15 0.059 g of azobisisobutyronitrile (AIBN) were added.
AIBN was recrystallized from ethanol before use. The
solution was then deoxygenated using nitrogen for
15 minutes and then placed under a passive nitrogen
blanket. After stirring for 16 hours at 60°C the
20 percent conversion was determined to be 95-98% by near
infrared (NIR) analysis. The number average molecular
weight was determined by size exclusion chromatography
vs. polystyrene and by end group titration. The Mn
values were 2,895 and 2,083 respectively. The
25 polydispersity of the copolymer was 1.5.

EXAMPLES 12-17

30 Copolymerization of 1H,1H,5H
 Octafluoropentylmethacrylate and Methoxy polyethylene
 glycol monomethacrylates

Example 12

35 OFPM, 15 g, methoxy polyethylene glycol 1,000
monomethacrylate, 1 g 2-mercaptoethanol, 2.34 g, and

AIBN (recrystallized from ethanol), 0.164 g, were combined with 500 mL of a 1:1 mixture of THF and methanol(MEOH) in a 1 L, three-neck flask. The flask was also fitted with a magnetic stirrer and a reflux condenser. The mixture was stirred until all reagents were in solution. A slow stream of nitrogen was then used to deoxygenate the solution for 15 minutes. After 72 hours of reflux under a nitrogen atmosphere the conversion to copolymer was 99+% (by NIR analysis). Solvent was removed by flash evaporation leaving a viscous oil, which upon standing formed a wax-like solid. Values for Mn, Mw and Pd were determined vs. polystyrene, (Mn= 3,700, Mw= 6,300 and Pd= 1.72). Results are shown in Table II.

15

Examples 13-17

The procedure of Example 12 was repeated using methoxy polyethylene glycol monomethacrylate in different molecular weights and relative amounts as indicated in Table II which also summarizes the results obtained.

20

Table IIHYDROXY TERMINATED COPOLYMERS

Example #	Type	Composition	Conversion, % (by NIR)	time hrs	Mn	Mw	Pd
5	12	OFPPMA/Peo 400	95	48	2190	3400	1.56
	13	OFPPMA/Peo 1k	99	72	3700	6300	1.72
	14	OFPPMA/Peo 5k	90	72	10.5k	16.1k	1.52
	15	OFPPMA/Peo 5k	75	65	10k	12.6k	1.27
	16	OFPPMA/Peo 2k	79	65	-	-	-
15	17	OFPPMA/Peo 2k	95	48	3900	4800	1.22

EXAMPLES 18-21Surface Active Macromonomer Preparation

5

Example 18

Distilled glycidyl methacrylate, 1.83 g,
p-methoxyphenol, 2.5 mg (MEHQ), and two drops of
N,N-dimethyldodecylamine were added to the solution
from Example 7. The mixture was allowed to reflux
10 under a nitrogen atmosphere for 5 hours. The solution
was washed 3 times with dilute sodium carbonate
solution and once with water. The organic layer was
dried over magnesium sulfate, and toluene removed by
flash evaporation at reduced pressure. The residue,
15 18.12 g (85% yield), of viscous yellow macromonomer had
Mn values of 3,353 (by SEC vs. polystyrene) and 3,416
(by vapor phase osmometry, vpo). The polydispersity
(Pd) of the macromonomer was 1.9. Results are
summarized in Table III.

20

Examples 19-21

The procedure of Example 18 was repeated using the
solutions from Examples 8-10. The copolymers of
25 Examples 9-10 were isolated and redissolved in dioxane
for surface active macromonomer preparation. Results
obtained are shown in Table III.

Table III

SURFACE ACTIVE MACROMERS

Example #	Type	Composition	Solvent	Rxn time	Mn	Mn	Pd
5	18	OFFMA/Peo 1k	80/20	Toluene	5h	3353 6493	1.9
	19	OFFMA/Peo 1k	70/30	Toluene	5h	2057 4587	2.2
	20	OFFMA/Peo 1k	50/50	Dioxane	5h	2545 4351	1.7
	21	OFFMA/Peo 5k	80/20	Dioxane	5h	8142 12k	1.5
10							

EXAMPLES 22-27Surface Active Macromonomer Preparation

5

Example 22

Hydroxy terminated copolymer, 41.744 g (from Example 12), was dissolved in 225 mL of THF, in a 500 mL 3-neck flask fitted with a magnetic stirrer, a reflux condenser, and an addition funnel. Dibutyltin dilaurate, 1.57 g, and butylated hydroxy toluene, 10 mg, were added. Isocyanatoethyl methacrylate, 1.98 g (ICEM) in 25 mL CHCl_3 , was added dropwise. Following the addition the solution was heated to reflux. After 16 hours 0.2% ICEM was detected by infrared analysis. Methanol, 5 mL, was added to react with the slight excess of ICEM. Chloroform was then removed by flash evaporation. The residue was left under high vacuum overnight to remove residual solvent leaving 42.4 g of wax-like semisolid. Values for the Mn, Mw, and Pd were determined vs polystyrene standards. Results are summarized in Table IV.

Examples 23-27

25

The procedure of Example 22 was repeated using hydroxy terminated copolymers (dissolved in chloroform) from Examples 13-17. Results are shown in Table IV.

Table IVSURFACE ACTIVE MACROMERS

5	Example #	Type	Composition	Solvent	Time hrs	Mn	Mn	Pd
	22	OFPPMA/Peo 400	50/50	THF	16	2500	4600	1.8
	23	OFPPMA/Peo 1k	50/50	CHCl ₃	16	4000	6700	1.69
10	24	OFPPMA/Peo 5k	80/20	CHCl ₃	12	4100	4500	1.12
	25	OFPPMA/Peo 5k	50/50	CHCl ₃	16	9900	12.5K	1.26
	26	OFPPMA/Peo 2k	50/50	CHCl ₃	16	-	-	-
	27	OFPPMA/Peo 2k	80/20	CHCl ₃	16	3800	4500	1.19

EXAMPLE 28Surface Active Macromonomer Preparation

5 Distilled glycidyl methacrylate, 1.58 g,
p-methoxyphenol, 2.8 mg (MEHQ), and two drops of
N,N-dimethyldodecylamine were added to the solution
from Example 11. The mixture was allowed to reflux
under a nitrogen atmosphere for 5 hours. The solution
10 was washed 3 times with dilute sodium carbonate
solution and once with water. The organic layer was
dried over magnesium sulfate, and toluene was removed
by flash evaporation at reduced pressure. The residue,
17.64 g (84% yield), of viscous semi-solid macromonomer
15 had Mn values of 1,593 (by SEC vs. polystyrene) and
1,918 (by vapor phase osmometry, vpo). The
polydispersity of the macromonomer was 1.6.

EXAMPLE 29Surface Active Macromonomer Preparation

20 Hydroxy terminated copolymer, 3.14 g (from
25 Example 3), was dissolved in 90 mL of chloroform, in a
250 mL 3-neck flask fitted with a magnetic stirrer, a
reflux condenser, and an addition funnel. Dibutyltin
dilaurate, 3 drops and butylated hydroxy toluene, 3 mg,
were added. Isocyanatoethyl methacrylate, 89 uL (ICEM)
30 in 10 mL CHCl_3 , was added dropwise. Following the
addition the solution was heated to reflux. After
12.5 hours no ICEM could be detected by infrared
analysis. The reaction mixture was then slowly added
to 2 L of anhydrous ethyl ether and the solid
35 collected. After drying at 30°C under reduced pressure
the yield of macromer was 3 g. The Mn, Mw and Pd

values were 4,900, 5,900 and 1.2 (vs. polyethylene glycol standards).

5

EXAMPLE 30Surface Active Macromonomer Preparation

Hydroxy terminated copolymer, 4.5 g, (from
10 Example 6) was dissolved in 90 mL of chloroform in a
250 mL 3-neck flask fitted with a magnetic stirrer, a
reflux condenser, and an addition funnel. Dibutyltin
dilaurate, 2 drops and butylated hydroxy toluene, 3 mg,
were added. Isocyanatoethyl methacrylate, 93 uL (ICEM)
15 in 10 mL CHCl_3 , was added dropwise. Following the
addition the solution was heated to reflux. After
20 hours a trace of ICEM could be detected by infrared
analysis. The reaction mixture was then slowly added
to 2 L of anhydrous ethyl ether and the solid
20 collected. After drying at 30°C under reduced pressure
the yield of macromer was 3.14 g. The Mn, Mw and Pd
values were 4,900, 8,900 and 1.8 (vs. PEG standards).

25

EXAMPLES 31-42Surface Tension Determination Using
the Wilhelmy Plate Technique

30

Macromonomer solutions were prepared with
distilled water at molar concentrations of 10^{-2} - 10^{-6} .
The surface tension of each solution was measured by
the Wilhelmy Plate technique on a Wettek, model
SFA-212, instrument. A test solution was placed in a
35 jacketed beaker, which had been cleaned with
chromic sulfuric acid for 40 minutes, rinsed with clean

water and dried overnight at 120°C. Data was collected by dipping a glass cover slip (cleaned by passing through a flame) into each solution several times at the following conditions:

5

Platform speed	0.16 mm/sec
Immersion depth	20.0 mm
Temperature	34 ± 1°C

- 10 The data was analyzed using WETTEK 12 software. Results are shown below in Table V.

Table VSURFACE TENSION DATA

	Example #	Macromer example #	Molar conc.	Temp. #C	Surface Tension dyne/cm
5	10	31	7	10 ⁻²	32.3
		32	7	10 ⁻³	34.8
		33	7	10 ⁻⁴	46.8
15	15	34	5	10 ⁻³	36.3
		35	5	10 ⁻⁴	46.2
		36	5	10 ⁻⁵	57.5
		37	5	10 ⁻⁶	66.8
		38	6	10 ⁻²	31.8
		39	6	10 ⁻³	34.3
20	20	40	6	10 ⁻⁴	38.7
		41	6	10 ⁻⁵	53.1
		42	6	10 ⁻⁶	65.9

EXAMPLE 43Polyurethane Monomer Mix

5

A urethane prepolymer prepared from isophorone diisocyanate, diethylene glycol, polysiloxanediol (molecular wt. 3,000) and endcapped with 2-hydroxyethyl methacrylate was combined with the following;

10 methacryloyloxypropyl tris(trimethylsiloxy)silane (TRIS), N,N-dimethylacrylamide (DMA), N-hexanol, benzoin methyl ether (BME). The proportions are given below.

15	Urethane prepolymer	35 parts
	TRIS	35 parts
	DMA	30 parts
	N-hexanol	40 parts
	BME	0.2 parts

20

The resulting clear mix was then filtered through a 1.2 micron filter into a clean glass vial.

25

EXAMPLE 44Polyurethane Monomer Mix ContainingSurface Active Macromer (SAM)

30

A monomer mix was prepared as in Example 43 except that 0.25 parts by weight of SAM 80/20 (Example 18) was added.

EXAMPLE 45Polyurethane Monomer Mix Containing SAM

5 A monomer mix was prepared as in Example 43 except that 0.25 parts by weight of SAM 50/50 (Example 20) was added.

10

EXAMPLE 46Polyurethane Monomer Mix Containing SAM

15 A monomer mix was prepared as in Example 43 except that 0.25 parts by weight of SAM 80/20 5k (Example 23) was added.

20

EXAMPLE 47Polyurethane Monomer Mix Containing SAM

25 A monomer mix was prepared as in Example 43 except that 0.25 parts by weight of SAM (Example 29) was added.

EXAMPLE 48Polyurethane Monomer Mix Containing SAM

5 A monomer mix was prepared as in Example 30 except that 0.25 parts by weight of SAM (Example 30) was added.

10

EXAMPLE 49Polyurethane Monomer Mix Containing
Monoperfluorooctyl Itaconic Acid

15 A monomer mix was prepared as in Example 43 except that 1 part by weight of monoperfluorooctyl itaconic acid was added.

20

EXAMPLE 50Vinyl Carbonate Monomer Mix

A solution was prepared by combining 3-
25 [tris(trimethylsiloxy)silyl]propyl vinyl carboxamide (TRISV), 1-vinyl-2-pyrrolidinone (NVP), pentacontamethyl-a,w-bis (4-vinyloxy-carbonyloxybutyl)pentacosyl siloxane (V2D25, Mw range 2-4k), nonanol, and
30 2-hydroxy-2-methyl-1-phenylpropan-1-one (DarocurR).
The proportions (by weight) are listed below.

	TRISV	55 parts
	NVP	30 parts
	V2D25	15 parts
5	Nonanol	10 parts
	DarocurR	0.2 parts

The solution was filtered into a glass vial.

10

EXAMPLE 51

Vinyl Carbonate Monomer Mix Containing SAM

15 A monomer mix was prepared as in Example 50 except that 0.36 parts by weight of SAM 80/20 5k (Example 24) was added.

20


EXAMPLE 52

Fluorosilicone Prepolymer Mix

25 Dimethylacrylate-capped polysiloxane with fluoroalkyl side chains $M_2D_{35}F_{65}$ as described in U.S. Patent 4,810,764 (fluorosilicone), octafluoropentylmethacrylate (OFPMA), 2-vinyl-4,4-dimethyl-2-oxazalin-5-one (VDMO), and benzoin methyl ether (BME) were combined in the weight
30 proportions shown below.

	Fluorosilicone	98 parts
	OFPMA	2 parts
	VDMO	5 parts
35	BME	0.2 parts

The resulting solution was filtered. The fluorosilicone monomer employed is described by the formula



10 wherein A is a methacrylate group; R_1 , R_2 and R_3 are methyl groups; R_4 is a trifluoropropyl group; m is 36; and n is 65.

15

EXAMPLE 53**Fluorosilicone Prepolymer Mix Containing SAM**

A monomer mix was prepared as in Example 52 except
20 that 0.25 parts by weight of SAM 80/20 5k (Example 24) was added.

25

EXAMPLE 54**Fluorosilicone Prepolymer Mix Containing SAM**

A monomer mix in Example 52 except that VDMO was
30 replaced with SAM 80/20 5k (Example 24).

30

EXAMPLE 55-66Contact Lens Cast Molding

5 Anterior and posterior mold surfaces were cleaned
by electrostatic deionization in air and transferred to
an inert (nitrogen) atmosphere. The mold anterior was
then filled with 40-80 uL of monomer mix,
(Examples 43-54) in the inert atmosphere and placed on
10 a casting plate. The mold posterior was then
positioned. Once the casting plate was full the top
plate was aligned and tightened down to 18 inch-pounds.
Casting plates were then placed under ultraviolet light
at 4,000 u watts/cm², (oxygen level was <50ppm), for one
15 hour. Following separation the mold halves containing
lenses were placed in a 70/30 volume/volume solution of
ethanol and water or 100% ethanol. Lenses and solution
were placed in an ultrasonic bath at 50°C and allowed
to release. Lenses were then transferred to absolute
20 ethanol. After one hour the solvent was exchanged with
fresh ethanol and allowed to stand for 48 hours.
Ethanol was then removed by water extraction.

25

EXAMPLE 67

Analysis for Surface-Active Macromer at Contact Lens
Surface Electron spectroscopy for chemical analysis
(ESCA)

30

Electron spectroscopy for chemical analysis (ESCA)
utilizes a monochromatic source of low energy x-ray to
produce a core level ionization. The energies of the
ejected photons are measured and subtracted from that
35 of the incident photon to obtain their binding

energies. These energies identify the elements present at or near the sample surface.

5 The polyurethane lens of Example 56 was subjected to ESCA analysis at x-ray incident angles of 15, 45, and 90 degrees. The smaller the incident angle, the shallower the probe depth of the sample surface. The atomic percent concentration of fluorine at the different incident angles was 5.33, 3.38 and 3.33%,
10 respectively. These data for the fluorine atom are indicative of a high concentration of surface-active macromer at the lens surface because the concentration of total macromer in the lens sample was only 0.25 weight %.

15

EXAMPLE 68

Analysis for Surface-Active Macromer at Contact Lens Surface Contact Angle

20

The contact angle of the surface of contact lenses prepared in Examples 55, 56, 57, and 59 were measured by the captive bubble technique. The lenses were submerged in buffered saline solution and a bubble of
25 air was attached to the undersurface of the lens. The angle made by the intersection of the lens and bubble surfaces was measured using a goniometer. The lower the contact angle the more hydrophilic or water wettable is the lens surface. Results are shown in
30 Table VI. Note that the lens of Example 55 contained no polymerizable surfactant. Addition of polymerizable surfactant as in Examples 56, 57, and 59 caused a marked reduction in the contact angle.

Table VI

	<u>Example No.</u>	<u>Contact Angle</u>
5	55	35
	56	20
	57	14
	59	24

10

EXAMPLE 69Clinical Evaluation of Example 58

15 Five subjects wore one contact lens of Example 58
(containing the polymerizable surfactant of Example 23)
in one eye and one control contact lens, Example 55
(without polymerizable surfactant) in the other eye.
The lenses were analyzed after a minimum of one hour of
20 wear for surface characteristics of wettability and
surface deposition. The wettability rating scale was
0-4, where 0 was more than 2/3 of the anterior lens
surface unwetted by tear film and 4 represented
complete (100%) wetting by tear film. The deposition
25 scale was 0-4 where 0 represented no surface deposits
and 4 was multiple deposits of 0.5 mm diameter or
larger. The results for the lenses of Example 58 were
wettability 3.2 and deposits 1.0 compared to 2.0 and
1.6, respectively, for the control lenses of
30 Example 55.

EXAMPLE 70

35

Clinical Evaluation of Example 63

Six subjects wore contact lenses of Example 63
(prepared from the monomer mix of Example 51 and
containing the polymerizable surfactant of Example 24)

in both eyes for a period of one hour and the lenses were analyzed as in Example 69. The results were wettability 3.2 and deposits 0.1 which compares favorably to values of 2.0 and 1.6, respectively for wettability and deposits for control lenses of Example 62 (which contained no polymerizable surfactant).

EXAMPLE 71

Clinical Evaluation of Example 57 (1K 50/50 PEOSAM)

Eight subjects wore one contact lens of Example 57 (prepared from the monomer mix of Example 45 and containing the polymerizable surfactant of Example 20) and one control contact lens, Example 55 (without polymerizable surfactant), in the other eye. The lenses were analyzed as in Example 69 after a minimum of one hour of wear for surface characteristics of wettability and surface deposition. The results for the lenses of Example 57 were wettability 2.6 and deposits 1.2 which compares favorably to values of 2.1 and 1.7, respectively, for wettability and deposits for control lenses of Example 55.

EXAMPLE 72

Clinical Evaluation of Example 59 (80/20 NVPSAM)

Five subjects wore contact lenses of Example 59 (prepared from the monomer mix of Example 47 and containing the polymerizable surfactant of Example 29) for a period of one hour and the lenses were analyzed as in Example 69. The results were wettability 2.6 and deposits 1.4 which compares favorably to values of 2.0

and 1.6, respectively for wettability and deposits for control lenses of Example 55.

5

EXAMPLE 73Clinical Evaluation of Example 61 (MPFOI)

Ten subjects wore contact lenses of Example 61
10 (prepared from the monomer mix of Example 49) for a
period of six hours and the lenses were analyzed as in
Example 69. The results were wettability 2.8 and
deposits 0.8 which compares favorably to values of 2.0
and 1.6, respectively for wettability and deposits for
15 control lenses of Example 55.

EXAMPLE 7420 Clinical Evaluation of Example 56 (1K 50/50 PEOSAM)

Eight subjects wore one contact lens of Example 56
(prepared from the monomer mix of Example 44 and
containing the polymerizable surfactant of Example 18)
25 in the eye and one control contact lens, Example 55
(without polymerizable surfactant), in the other eye.
The lenses were analyzed as in Example 69 after a
minimum of one hour of wear for surface characteristics
of wettability and surface deposition. The results for
30 the lenses of Example 56 were wettability 2.6 and
deposits 1.2 which compares favorably to values of 2.1
and 1.7, respectively for wettability and deposits for
control lenses of Example 55.

What is claimed is:

1. A method of modifying the surface of a polymeric object which comprises adding a polymerizable
5 surfactant to the monomer mix used to form the polymeric object.
2. The method of claim 1 wherein the polymerizable surfactant is a surface active macromer described by
10 the formula:
$$DC[A_xB_y]$$
wherein A is at least one ethylenically unsaturated hydrophilic monomer, B is at least one ethylenically unsaturated hydrophobic monomer, C is a functional
15 chain transfer agent, and D is an ethylenically unsaturated end group.
3. The method of claim 2 wherein A is selected from the group consisting of ethylenically unsaturated
20 polyoxyalkylenes, polyacrylamides, polyvinylpyrrolidones, polyvinyl alcohols, poly (HEMA), and N-alkyl-N-vinyl acetamide.
4. The method of claim 2 wherein A is an
25 ethylenically unsaturated polyoxyalkylene selected from the group consisting of (meth)acrylated polyoxyalkylenes, (meth)acrylamido polyoxyalkylenes, styrenyl polyoxyalkylenes, alkenyl polyoxyalkylenes, vinyl carbonate polyoxyalkylenes and vinyl carbamate
30 polyoxyalkylenes.
5. The method of claim 4 wherein the polyoxyalkylene is polyethylene oxide.
- 35 6. The method of claim 2 wherein A is (meth)acrylated polyethylene oxide.

7. The method of claim 6 wherein A is methoxy polyethylene glycol methacrylate.
8. The method of claim 3 wherein A is a methacrylate
5 endcapped poly-N-vinylpyrrolidinone.
9. The method of claim 3 wherein A is a methacrylate endcapped poly-N,N-dimethylacrylamide.
10. The method of claim 2 wherein B is selected from the group consisting of alkyl (meth)acrylates, N-alkyl
10 (meth)acrylamides, alkyl vinylcarbonates, alkyl vinylcarbamates, fluoroalkyl (meth)acrylates, N-fluoroalkyl (meth)acrylamides, N-fluoroalkyl vinylcarbonates, N-fluoroalkyl vinylcarbamates, silicone-containing (meth)acrylates, (meth)acrylamides,
15 vinyl carbonates, vinyl carbamates, styrenic monomers and polyoxypropylene (meth)acrylates.
11. The of claim 10 wherein the styrenic monomers are selected from the group consisting of styrene, alpha-methyl styrene, para-methyl styrene, para-t-butyl
20 monochloro styrene, and para-t-butyl dichloro styrene.
12. The method of claim 10 wherein B is 1-H,1-H,5-H-octafluoropentyl methacrylate.
13. The method of claim 2 wherein C is selected from the group consisting of mercapto carboxylic acids,
25 mercapto alcohols, and aminomercaptans.
14. The method of claim 13 wherein C is thioglycolic acid.
15. The method of claim 13 wherein C is 2-mercaptoethanol.

16. The method of claim 13 wherein C is 2-aminoethane thiol.

17. The method of claim 14 wherein D is a
(meth)acrylated hydroxy ester moiety derived from
5 glycidyl (meth)acrylate.

18. The method of claim 15 wherein D is a
(meth)acrylated ester moiety derived from
(meth)acryloyl chloride.

19. The method of claim 15 wherein D is a
10 (meth)acrylated urethane moiety derived from
(meth)acrylated isocyanate.

20. The method of claim 16 wherein D is a
(meth)acrylated urea moiety derived from
(meth)acrylated isocyanate.

15 21. The method of claim 15 wherein D is a
vinylcarbonate moiety derived from vinyl chloroformate.

22. The method of claim 16 wherein D is a
(meth)acrylated amide moiety derived from
(meth)acryloyl chloride.

20 23. The method of claim 16 wherein D is a
vinylcarbamate moiety derived from vinyl chloroformate.

24. The method of claim 1 wherein the polymeric object
is a contact lens.

25 25. The method of claim 24 wherein the contact lens is
a hydrogel contact lens.

26. The method of claim 24 wherein the contact lens is
a rigid gas permeable lens.

27. The method of claim 24 wherein the contact lens is
a silicone elastomer contact lens.

28. The method of claim 1 wherein the cross-linking agent is selected from the group consisting of hydrophobic molecules having two or more polymerizable groups.
- 5 29. A surface-modified polymeric object prepared by adding a polymerizable surfactant to the monomer mix used to form the polymeric object.
30. The surface-modified object of claim 29 wherein the object is a contact lens.

International Application No.

I. CLASSIFICATION OF SUBJECT MATTER (If several classification symbols apply, indicate all)⁶

Int.Cl. 5 C08F299/00; G02B1/04

Minimum Documentation Searched?

Classification Symbols

C08F ; G02B

Documentation Searched other than Minimum Documentation
to the Extent that such Documents are Included in the Fields Searched⁸

Relevant to Claim No.13

A US,A,4 075 411 (DICKSTEIN) 21 February 1978
cited in the application

"&" document member of the same patent family

MEULEMANS R.A.M.

ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO. US 9108731
SA 54892

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. 19/03/92

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0248574	09-12-87	JP-A- 62277408 US-A- 4952638	02-12-87 28-08-90
US-A-4075411	21-02-78	None	